

P₂O₅/Al₂O₃ as an efficient catalyst for one-pot synthesis of polyhydroquinoline derivatives under solvent-free conditions

Tayebeh Sanaeishoar^{1*}, Sara Roueen²

¹ *Young Researchers Club, Khouzestan Science and Research Branch, Islamic Azad University, Ahvaz, Iran, t.sanaei@khouzestan.srbiau.ac.ir*

² *Department of chemistry, College of Science, Khouzestan Science and Research Branch, Islamic Azad University, Ahvaz, Iran*


Abstract- The condensation of aromatic aldehydes, dimedone, ethylacetoacetate and ammonium acetate promoted by was Phosphorus pentoxide supported on alumina carried out under solvent-free conditions to afford corresponding polyhydroquinoline derivatives. This method provides several advantages including high yields, low reaction times, easy work up and little catalyst loading.

Keywords: Polyhydroquinoline, Solvent-free, Multicomponent reactions, Phosphorus pentoxide supported on alumina

Introduction

In recent years, great attention has been paid to the synthesis of polyhydroquinolines because of its highly absolute biological and physiological activities such as calcium channel blockers, asodilator, hepatoprotective, anti atherosclerotic, bronchodilator, anti tumor, geroprotective, antidiabetic activity, etc [1]. In addition, these compounds have found wide usage in drugs including nifedipine, nicardipine and amlodipine [2]. Recently, the synthesis of polyhydroquinolines has been achieved by the condensation of aromatic aldehydes, dimedone, ethylacetoacetate and ammonium acetate in the presence of various catalysts, such as L-proline [3], PEG-400 [4], microwave [5], PTSA [6], tin dioxide nanoparticles [7], copper perchlorate hexahydrate [8], 1,3-dibromo-5,5-dimethylhydantoin (DBH) [9], alumina sulfuric acid (ASA) [10], molybdenum(VI) complex [11], t-BuOK [12], cobalt nanoparticles [13], aqueous media [14], ionic liquid [15], (NH₄)₆[Mn^{IV}Mo₉O₃₂] [16], liquid phase [17], Amberlite IR-120 [18], Nafin-H [19] and ZrCl₄ [20].

In view of the above observation, we decided to develop an environmentally and green approach for the synthesis of some polyhydroquinolines catalyzed by Phosphorus pentoxide supported on alumina solvent-free neat conditions (Scheme 1).



Scheme 1

Experimental

All chemicals were purchased from Merck and used without further purification. IR spectra were recorded on a Shimadzu IR-460 spectrometer. ¹H spectra were recorded on a Bruker DRX-300 AVANCE instrument with CDCl₃ as solvent.

General procedure for the synthesis of polyhydroquinolines.

A mixture of dimedone (1 mmol), benzaldehyde (1 mmol), ethylacetoacetate (1 mmol), ammonium acetate (1 mmol) and Phosphorus pentoxide supported on alumina (8 % mol) was stirred at 110 °C for the appropriate time (monitored by TLC). On completion of reaction, the reaction mixture was cooled and was triturated with 10 mL of dichloromethane to get the solid product. The product obtained was filtered, washed with cold water, dried, and recrystallized from ethanol and water.

Ethyl 1,4,5,6,7,8-hexahydro-4-(phenyl)-7,7-dimethyl-5-oxoquinoline-3-carboxylate (**5a**): M.P. 205-207°C, ¹H NMR (300 MHz, CDCl₃): δ ppm = 0.91 (s, 3H, CH₃), 1.05 (s, 3H, CH₃), 1.17 (t, J=7.1 Hz, 2H, CH₂), 2.14-2.20 (m, 4H, 2CH₂), 2.28 (s, 3H, CH₃), 4.03 (q, J=7.1 Hz, 3H, CH₃), 5.02 (s, 1H, CH), 5.96 (s, 1H, CH), 7.04-7.09 (m, 1H, CH), 7.14-7.19 (m, 2H, CH), 7.23-7.26 (m, 2H, CH₂). ¹³C NMR (CDCl₃, 75 MHz): δ ppm = 14.18, 19.45, 27.16, 29.41, 32.72, 36.53, 41.16, 50.70, 59.81, 100.33, 106.29, 112.61, 126, 127.86, 143.83, 146.99, 147, 167.68, 195.75; IR (KBr, cm⁻¹): 3289, 3080, 2959, 1698, 1610.

Ethyl 1,4,7,8-tetrahydro-2,7,7-trimethyl-4-(4-methoxyphenyl)-5(6H)-oxoquinolin-3-carboxylate (**5f**): M.P. 258-260 °C: ¹H NMR (300 MHz, CDCl₃): δ ppm 0.95 (s, 3H, CH₃), 1.09 (s, 3H, CH₃), 1.21 (t, J=7.2 Hz, 3H, CH₃), 2.01-2.10 (m, 4H, 2CH₂), 2.30 (s, 3H, CH₃), 3.70 (s, 3H, OCH₃), 4.00 (q, J=7.2 Hz, 2H, CH₂), 4.80 (s, 1H, CH), 6.65 (d, J=7.3 Hz, 2H, ArH), 7.10 (d, J=7.3 Hz, 2H, ArH), 8.65 (s, 1H, NH); ¹³C NMR (CDCl₃, 75 MHz): δ = 195.7, 167.5, 157.7, 149.1, 142.9, 139.8, 128.9, 113.7, 113.3, 106.4, 59.8, 55.1, 37.0, 35.4, 27.5, 21.1, 19.4, 14.2; IR (KBr, cm⁻¹): 3276, 2956, 1703, 1648, 1606, 1496, 1381, 1215, 1031, 765.

Result and Discussion

In the initial experiments, the effect of reaction temperature was examined using the reaction of aromatic aldehydes, dimedone, ethylacetoacetate and ammonium acetate in the presence of 8 % mol of Phosphorus pentoxide supported on alumina under solvent-free conditions. As can be seen from Table 1, the optimum temperature was at 110 °C. The effect of the amount of catalyst was also examined. It was found that the use of 8 mol % of Phosphorus pentoxide supported on alumina was sufficient to progress the reaction. Although an increase of the amount of catalyst lead to short reaction time, reductive yields also were observed.

Table1. Effect of different reaction conditions for the condensation of aromatic aldehydes, dimedone, ethylacetoacetate and ammonium acetate under solvent free

ENTRY	TEMPERATURE (°C)	AMOUNT OF CATALYST (MOL%)	TIME (MIN)	YIELD (%)
1	70	8	15	70
2	80	8	10	75
3	100	8	6	90
4	110	8	2	95
5	110	4	2	90
6	110	15	2	80
7	110	20	3	85


As can be seen from Table 2, dimedone, ethylacetoacetate and ammonium acetate with various aromatic aldehydes at 110 °C using 8 mol% of Phosphorus pentoxide supported on alumina as catalyst, carrying either electorn-donating or electron-withdrawing substituents, gave the corresponding polyhydroquinolines under solvent-free condition in excellent yields.

Table2. Synthesis of substituted polyhydroquinolines

ENTRY	AR	PRODUCT	TIME(MIN)	YIELD (%)	M.P (°C)	REF.M.P(°C)
-------	----	---------	-----------	--------------	----------	-------------

1	C ₆ H ₅	5A	120	84	208-210	202-204 ^[6]
2	3-NO ₂ C ₆ H ₄	5B	90	86	170-172	178-180 ^[9]
3	4-NO ₂ C ₆ H ₄	5C	90	88	242-244	242-244 ^[8]
4	4-CLC ₆ H ₄	5D	90	76	238-241	244-246 ^[10]
5	4-CH ₃ C ₆ H ₄	5E	90	70	254-258	265-268 ^[11]
6	4-	5F	90	72	250-254	257-259 ^[20]
7	OMEC ₆ H ₄	5G	90	90	149-151	143-145 ^[7]
	4-CNC ₆ H ₄					

A tentative mechanism to rationalize the product formation is shown in scheme2. Polyhydroquinoline **5** may be formed either through steps (I—III) or through steps (IV—V). The role of Phosphorus pentoxide supported on alumina (Lewis Acid) comes in steps (I) and (IV), where it catalyzes the Knoevenagel type coupling of aldehydes with active methylene compounds and in steps (III) and (VI), where it catalyzes the Michael type addition of intermediates **6**, **7** and **8**, **9** to give product **5**.



Scheme 2

Conclusions

This report describes an efficient procedure for the synthesis of polyhydroquinolines derivatives by solid phase catalyst with improved yields. This procedure offers several advantages including high yields, low reaction times, easy work up and little catalyst loading,

cleaner reaction, high yields of products as well as a simple experimental and work-up procedure which makes it a useful, economical and waste-free process for the synthesis of these compounds. So we can say this method is faster and easier than other published method.

REFERENCES

- [1] J. R. Safari, S. H. Banita and S. Dehghan Khalil, Nano crystalline copper(II) oxide-catalyzed one-pot four component synthesis of polyhydroquinoline derivatives under solvent-free conditions, *J. Nano. Struct.*, 2012, **1**, 243-248.
- [2] S. Pendkar, R. Bhalerao and N. Ghadge, One-pot multi-component synthesis of 1,4-dihydropyridine derivatives in biocompatible deep eutectic solvents, *N. J. Chem. Sci.*, 2013, **3**, 615-621.
- [3] F. K. Behbahani and M. Mohammadloo, L-proline-catalyzed synthesis of fused dihydropyridines through Hantzsch reaction, *Eur. Chem. Bull.*, 2013, **11**, 916-919.
- [4] N. V. Shitolea, B. V. Shitole, G. K. Kakde and M. S. Shingareb, PEG-400 as an efficient and recyclable reaction medium for the synthesis of polyhydroquinolines via Hantzsch reaction, *Orbital Elec. J. Chem.*, 2013, **9**, 679-682.
- [5] V. M. J. Kumar and R. P. Pawar, Microwave assisted expeditious synthesis of bioactive polyhydroquinoline derivatives, *Eur. Chem. Bull.*, 2005, **46**, 5771-5774.
- [6] S. R. Cherkupally and R. Mekala, P-TSA catalyzed facile and efficient synthesis of polyhydroquinoline derivatives through Hantzsch multi-component condensation, *Chem. Pharm. Bull.*, 2008, **7**, 1002-1004.
- [7] S. M. Vahdat, F. Chekin, M. Hatami, M. Khavarpour, S. Bagheri and Z. Roshan-Kouhi, Synthesis of polyhydroquinoline derivatives via a four component Hantzsch condensation catalyzed by tin dioxide nanoparticles, *Chin. J. Catal.*, 2009, **50**, 1754-1756.
- [8] S. Puri, B. Kaur, A. Parmar and H. Kumar, Copper Perchlorate Hexahydrate an efficient catalyst for the green synthesis of polyhydroquinolines under ultrasonication, *ISRNOrg. Chem.*, 2011, **2011**, 1-4.
- [9] F. Shirini, Gh. Imanzadeh, M. Abedinia and P. Ghods Ghasemabadi, 1,3-Dibromo-5,5-dimethylhydantoin (DBH) as a cheap and efficient catalyst for the synthesis of polyhydroquinolines and 12-aryl-8,9,10,12-tetrahydro [a] xanthene-11-ones, *Iran. J. Catal.*, 2013, **2**, 57-65.
- [10] M. Arslan, C. Faydali, M. Zengin, M. Küç ükislamoğlu and H. Demirhan, An efficient one-pot synthesis of 1,4-dihydropyridines using alumina sulfuric acid (ASA) catalyst, *Turk. J. Chem.*, 2009, **33**, 769 - 774.

- [11] H. Khabazzadeh, I. Sheikhshoae and S. Saeid-Nia, A molybdenum(VI) complex as an efficient catalyst for the synthesis of dihydropyridines, *Transition Met. Chem.*, 2010, **35**, 125-127.
- [12] A. Debache, L. Chougaiat, R. Boulcina and B. Carbonib, A one-pot multi-component synthesis of dihydropyrimidinone/thione and dihydropyridine derivatives via Biginelli and Hantzsch condensations using t-BuOK as a catalyst under solvent-free conditions, *The Open Org. Chem. J.*, 2012, **6**, 12-20.
- [13] J. R. Safari, S. H. Banitaba and S. DehghanKhalili, Cobalt nanoparticles promoted highly efficient one-pot four-component synthesis of 1,4-Dihydropyridines under solvent-free conditions, *Chin. J. Catal.*, 2011, **12**, 1850–1855.
- [14] B. P. Bandgar, P. E. More, V. T. Kamble and J. V. Totre, Synthesis of polyhydroquinoline derivatives under aqueous media, *Arkivoc*, 2008, **XV**, 1-8.
- [15] J. P. Nirmal, P. V. Dadhania, M. P. Patel and R. G. Patel, A facile four component one-pot synthesis of polyhydroquinoline derivatives catalyzed by ionic liquid via modified Hantzsch reaction, *Indian. J. Chem.*, 2010, **49B**, 587-592.
- [16] A. R. Supale and G. S. Gokavi, Waugh type Enneamolybdomanganate(IV) catalyzed synthesis of polyhydroquinoline through Hantzsch multi-component condensation, *The Open Catal. J.*, 2009, **2**, 61-65.
- [17] X-L. Zhang, S-R. Sheng and X-L. Liu, Solvent-free liquid-phase synthesis of polyhydroquinoline derivatives under microwave irradiation, *Arkivoc*, 2007, **XIII**, 79-86.
- [18] R. Pallavi, K. Ritu and O. Srinivas, Amberlite IR-120 catalyzed one-pot four component Hantzsch reaction for the synthesis of 1,4-dihydropyrimidines, *Chem. Bio. Interface*, 2013, **1**, 38-49.
- [19] M. Kidwai, R. Chauhan, D. Bhatnagar, A. K. Singh, B. Mishra and S. Dey, Nafion-H⁺ catalyzed synthesis of polyhydroquinolines via the Hantzsch multicomponent reaction, *Monatsh. Chem.*, 2012, **143**, 1675-1680.
- [20] Ch. Sanjeeva Reddy and M. Raghu, Facile ZrCl₄ promoted four-component coupling one-pot synthesis of polyhydroquinoline derivatives through unsymmetric Hantzsch reaction, *Indian. J. Chem.*, 2008, **47B**, 1578-1582.